

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 16 Sept 97	3. REPORT TYPE AND DATES COVERED Final 01 June 94 - 31 May 96	
4. TITLE AND SUBTITLE Monte Carlo Simulation of Mercury Cadmium Telluride			5. FUNDING NUMBERS DAAH04-94-G-0187	
6. AUTHORS M. Shur and B. Gelmont				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Virginia Office of Sponsored Programs P. O. Box 9003 Charlottesville, Virginia 22906			8. PERFORMING ORGANIZATION REPORT NUMBER 5-25033	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P. O. Box 12211 Research Triangle Park, North Carolinda 27709-2211			10. SPONSORING/MONITORING AGENCY REPORT NUMBER ARO 32476.9-EL	
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) <i>We derived basic equations for basic electron scattering processes in narrow band gap semiconductors. However even in the case when the relaxation time approximation can be introduced a set of cumbersome integrals has to numerically calculated for intermediate degeneracy of an electron gas which is characteristic for narrow band gap semiconductors at liquid nitrogen temperature. As to the scattering by optical phonons the standard relaxation time approximation is, in general, not applicable.</i>				
14. SUBJECT TERMS electron scattering processes, polar optical phonon mobility, semiconductor			15. NUMBER OF PAGES 4	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	

19971204 084

FINAL TECHNICAL REPORT

1. ARO PROPOSAL NUMBER: 32476-EL
2. PERIOD COVERED BY REPORT: June 1, 1994 through May 31, 1996
3. TITLE OF PROPOSAL: Monte Carlo simulation of Mercury Cadmium Telluride
4. CONTRACT OR GRANT NUMBER: DAAH04-94-G-0187
5. NAME OF THE INSTITUTION: University of Virginia, Charlottesville
6. AUTHORS OF REPORT: B. Gelmont and M. Shur
7. LIST OF MANUSCRIPTS SUBMITTED OR PUBLISHED UNDER FULL OR PARTIAL ARO SPONSORSHIP DURING THIS REPORTING PERIOD:

B. Gelmont, M. S. Shur, and M. Strosio, Polar Optical phonon scattering in three- and two-dimensional electron gases, J. Appl. Phys., 77 (2), pp. 657-660, 15 Jan. (1995)

A. Bykhovski, B. Gelmont, M. S. Shur, and A. Khan, Current-Voltage Characteristics of Strained Piezoelectric Structures, J. Appl. Phys., vol. 76, Feb. 15, p. 1616-1620 (1995)

B. Gelmont, M. S. Shur, and R. J. Mattauch, Disk and Stripe Capacitances, Solid State Electronics, vol. 38, No. 3, pp. 731-734 (1995)

M. Dyakonov and M. S. Shur, Choking of Electron Flow - A Mechanism of Current Saturation in Field Effect Transistors, Phys. Rev. B, vol. 51, No. 20, pp. 14341-14345, 15 May (1995)

T. Fjeldly and M. S. Shur, Simulation and Modeling of Compound Semiconductor Devices, International Journal of High Speed Electronics and Systems, vol. 6, No. 1, pp. 237-284 (1995)

B. Gelmont and M. S. Shur, Hall Factor for Ionized Impurity Scattering, J. Appl. Phys., vol. 78, N4, Aug. 15, pp. 2846-2847 (1995)

M. I. Dyakonov and M. S. Shur, Two Dimensional Electronic Flute, Applied Physics Letters, vol. 67 (8), August 21, pp. 1137-1139, 1995

M. I. Dyakonov and M. S. Shur, Terahertz Devices using Two Dimensional Electron Fluid: Sources, Detectors, Multipliers, and Mixers, in Proceedings of International Semiconductor Device Research Symposium, vol. II, pp. 455-458, Charlottesville, VA, ISBN 1-880920-04-4, Dec., 1995 (invited)

B. L. Gelmont, M. S. Shur, and R. J. Mattauch, Theory of Dark Resistance in Photodiodes for Arbitrary Diode Geometry, in Proceedings of International Semiconductor Device Research Symposium, vol. I, pp. 277 - 280, Charlottesville, VA, ISBN 1-880920-04-4, Dec., 1995

M. E. Levinshtein and M. S. Shur, Editors, Best of Soviet Semiconductor Physics and Technology (1989-1990), World Scientific, Singapore (1995)

M. Shur, B. Gelmont, and A. Khan, Electrons Gas in AlGaIn/GaN Heterostructures and in Bulk GaN, J. Electronic Materials, vol. 25, No. 5, pp. 777-785 May (1996)

M. I. Dyakonov and M. S. Shur, Field Effect Transistor as Two Dimensional Electronic Flute, pp. 251-262, in Proceedings of NATO Advanced Research Workshop, Ile de Bendor, France, July (1995), Future Trends in Microelectronics. Reflection on the Road to nanotechnology, edited by Serge Luryi, Jimmy Xu, and Alex Zaslavsky, NATO ASI series, Series E: Applied Sciences - vol. 323, Kluwer Academic Publishers, Dordrecht/ Boston/ Lisbon (1996)

M. I. Dyakonov and M. S. Shur, Detection, Mixing, and Frequency Multiplication of Terahertz Radiation by Two Dimensional Electronic Fluid, IEEE Transactions on Electron Devices, vol. 43, No. 3, pp. 380-387, March (1996)

M. I. Dyakonov and M. S. Shur, Plasma Wave Electronics: Novel Terahertz Devices using Two Dimensional Electron Fluid, Special Issue on Future Directions in Device Science and Technologies, IEEE Transactions on Electron Devices, vol. 43, No. 10, pp. 1640-1646, October (1996)

T. Fjeldly, T. Ytterdal, and M. S. Shur, Metal Semiconductor Field Effect Transistors, in "Compound Semiconductor Technology. The Age of Maturity", World Scientific, 1996, ed. M. S. Shur, ISBN 981-02-2325, pp. 1-24

T. Fjeldly and M. S. Shur, Simulation and Modeling of Compound Semiconductor Devices, in "Compound Semiconductor Technology. The Age of Maturity", World Scientific, 1996, ed. M. S. Shur, ISBN 981-02-2325, pp. 317-364

T. A. Fjeldly, Michael S. Shur and T. Ytterdal, Device Modeling Issues in Deep-Submicron MOSFETs, Semiconductor International, pp. 131-142 June (1996)

M. E. Levinshtein, S. Rumyantsev, and M. Shur, Editors, Handbook of Semiconductor Material Parameters, vol. 1, World Scientific, 1996

K. Weiser, F. Dahan, S. E. Schacham, M. Shur, E. Towe, and H. Park, Laser Beam Interference Effects on the Photovoltage of a p-n Junction Diode, J. Appl. Phys., Vol. 80, Issue 9, pp. 5459-5463, November 1, 1996

8. SCIENTIFIC PERSONNEL SUPPORTED BY THIS PROJECT:

B. Gelmont, Senior Scientist

M. I. Dyakonov, Visiting Scientist

BRIEF OUTLINE OF RESEARCH FINDINGS

We derived basic equations for basic electron scattering processes in narrow band gap semiconductors. However even in the case when the relaxation time approximation can be introduced a set of cumbersome integrals has to be numerically calculated for intermediate degeneracy of an electron gas which is characteristic for narrow band gap semiconductors at liquid nitrogen temperature. As to the scattering by optical phonons the standard relaxation time approximation is, in general, not applicable.

Hence, we started from deriving an analytical equation for the polar optical phonon mobility, which is valid when the electron thermal energy is much smaller than the optical phonon energy. We also took into account the effects of the nonparabolicity which include the change of the dispersion law and the interband mixing of wave functions. We calculated the polar optical phonon mobility of the 2D-gas near insulator-semiconductor heterostructure in Metal-Insulator-Semiconductor (MIS) structure. Then we have developed simple analytical approximations for basic electron scattering processes in semiconductors at any degree of degeneracy. We have considered three most important scattering processes: by impurities, by polar optical phonon and due to piezoelectric interaction with acoustical phonons. We apply our new approach for the calculation of transport characteristics of a wide band gap semiconductor GaN which has a great potential for application in high power and optoelectronic devices. The Hall and drift mobility electrons in bulk GaN as well and in the 2D-gas at AlGaIn/GaN heterointerface have been calculated. This calculation required us to develop a new analytical theory of the Hall factor for impurity scattering -- a classic problem which has attracted attention since early 50s. We proposed an analytical equation describing the temperature and concentration dependencies of the Hall factor. We also demonstrated that the enhanced mobility of the 2D gas in GaN is caused by an enhanced electron screening. This work is joint with APA Optics, inc., and our results are in excellent agreement with experimental data. We have also developed analytical approximations for transport parameters which will be used in device simulation. In order to perform accurate device simulation without resorting to the time consuming Monte-Carlo simulation, we used a set of phenomenological balance equations including momentum and energy balance. At first it was necessary to have accurate and simple approximations for the transport parameters. For the calculation of transport parameters in GaAs and InP Monte-Carlo simulations were performed for wide range of electric field, temperature and impurity concentration. Then we have developed analytical approximations for transport parameters as functions of temperature, electric field and energy. These approximations can be used in device simulation. These results were submitted to Silvaco, Inc. for the incorporation in their device simulation ATLAS II.

Infrared focal plane arrays of photodetectors require small pixel size with uniform response over large areas. As the detector area decreases, surface and geometrical effects become increasingly important. In particular the zero-bias resistance of the photodetector has to be calculated taking into account the lateral spreading of the flow of the minority carriers. In practical photodetector arrays the layer thickness is comparable with the diffusion length. Since the absorption coefficient is relatively large and the light is absorbed near the surface, the collection of the photogenerated carriers improves when the junction is closer to the back surface of the device, i. e. when the layer thickness is decreased. On the other hand, the spreading resistance decreases with an increase in the layer thickness. Choosing the layer thickness to be on the order of the

diffusion length is a reasonable trade-off, since at such values of the layer thickness nearly all photogenerated carriers are collected by the junction. When the layer thickness is comparable to the diffusion length, analytical treatment does not apply. We developed a simple model, which is applicable when the layer thickness, b , and the diffusion length, L , are small in comparison with the detector radius. We also derived an integral equation, which is valid for any ratios of the layer thickness, the recombination length, and the detector radius. This equation can be easily solved by standard numerical techniques.

Our new approach allowed us to calculate the Hall and drift mobility electrons in bulk GaN as well and in the 2D-gas at AlGa_N/GaN heterointerface. This calculation required us to develop a new analytical theory of the Hall factor for impurity scattering -- a classic problem which has attracted attention since nearly 50s. We proposed an analytical equation describing the temperature and concentration dependencies of the Hall factor. We also demonstrated that the enhanced mobility of the 2D gas in GaN is caused by an enhanced electron screening. This work is joint with APA Optics, inc., and our results are in excellent agreement with experimental data.

In addition, the work has been done on general properties of surface electron plasma in heterostructures. We demonstrated that in typical 2D systems in compound semiconductors and even in silicon, electrons behave not as 2D-gas but rather as 2D fluid. The collective excitations of such a fluid are surface plasma waves that may become unstable under constant current conditions. This led to several new device concepts, including electronic flute, resonant and non-resonant plasma detectors, mixers, and terahertz oscillators. These devices should be able to push a three terminal device operation into a much higher frequency range than has been possible for conventional, transit time limited regimes of operation.